ASEC



FRICTION MATERIAL AB-3490

SKU: AB3490

ASEC Kunststoffen BV

Marketing 17, 6921 RE Duiven, The Netherlands

T: +31 316 84 44 01 | info@asec.nl

Categories: Organic moulded

Asbestos-free, rigid moulded, fully cured composite friction material. Bases on resins and rubber as bonding system, containing friction modifiers, mineral fibers and fine copper particles. AS 3460 is an alternative for sintered metal friction materials. It will resist high energy inputs and is suitable for dry and oil-immersed applications. AS 3460 is mediate abrasive to the counter face material. Application: High performance friction material suitable for heavy duty, wet and dry industrial applications such as forge industry, punch die press blocks, rings and segments. Recommended mating surface: pearlitic grey cast iron, but also steel qualities are permitted. Hardness between HB 150 and 200. Characteristics: Resistant to oil. The listed temperatures in this data sheet are average friction surface temperatures at the surface of brake lining and/or drum or disc. By the maximum permitted temperature (intermittent operation) is meant a peak value that might be reached in an emergency situation. Very high and stable fiction coefficient and excellent resistance to fading. Differences in color cannot be excluded due to natural raw materials. Suitable for bonding and riveting.

Extreme performance friction material. Resistant to high energy input. Suitable for heavy duty applications. Very low wear rate. High speed operation applications.

The information in this datasheet is provided for general purposes only and not meant to be a specific recommendation for any individual application. All values were determined under laboratory conditions. ASEC Products is not directly neither indirectly responsible for any claim resulting from the use of any information provided in this datasheet.
ASEC Products 2022 ©.

ASEC

The information in this datasheet is provided for general purposes only and not meant to be a specific recommendation for any individual application. All values were determined under laboratory conditions. ASEC Products is not directly neither indirectly responsible for any claim resulting from the use of any information provided in this datasheet.
ASEC Products 2022 ©.